



SPECIFICATION

(Reference sheet)

· Supplier : Samsung electro-mechanics · Samsung P/N: CL03B471KO3NNNH


· Product : Multi-layer Ceramic Capacitor · Description : CAP, 470pF, 16V, ±10%, X7R, 0201

A. Samsung Part Number

<u>CL</u> <u>03</u> <u>B</u> <u>471</u> <u>K</u> <u>O</u> <u>3</u> <u>N</u> <u>N</u> <u>N</u> <u>H</u> ① ② ③ ④ ⑤ ⑥ ⑦ ⑧ ⑨ ⑩ ⑪

1	Series	Samsung Multi-layer Ceramic Capacitor				
2	Size	0201 (inch code)	L: 0.60 ± 0.03 mm	W:	0.30 ± 0.03 mm	
3	Dielectric	X7R	Inner electrode		Ni	
4	Capacitance	470 pF	Termination		Cu	
(5)	Capacitance	±10 %	Plating		Sn 100% (Pb Free)	
	tolerance		Product		Normal	
6	Rated Voltage	16 V	Special		Reserved for future use	
7	Thickness	0.30 ± 0.03 mm	11) Packaging		Cardboard Type, 7" reel	

B. Structure & Dimension



Samoung D/N	Dimension(mm)					
Samsung P/N	L	W	Т	BW		
CL03B471KO3NNNH	0.60 ± 0.03	0.30 ± 0.03	0.30 ± 0.03	0.15 ± 0.05		

C. Samsung Reliablility Test and Judgement Condition

	Judgement	Test condition			
Capacitance	Within specified tolerance	1kHz ±10% / 1.0±0.2Vrms			
Tan δ (DF)	0.035 max.	*A capacitor prior to measuring the capacitance is heat treated at $150^{\circ}C+0/-10^{\circ}C$ for 1 hour and maintained in ambient air for 24±2 hours.			
Insulation	10,000Mohm or 100Mohm× <i>µ</i> F	Rated Voltage 60~120 sec.			
Whichever is smaller					
Appearance	No abnormal exterior appearance	Microscope (×10)			
Withstanding	No dielectric breakdown or	250% of the rated voltage			
oltage mechanical breakdown		-			
Temperature X7R					
Characteristics	(From-55℃ to 125℃, Capacitance chang	e should be within ±15%)			
Adhesive Strength	No peeling shall be occur on the	200g·f, for 10±1 sec.			
of Termination	terminal electrode				
Bending Strength	Capacitance change: within ±12.5%	Bending to the limit (1mm)			
		with 1.0mm/sec.			
Solderability	More than 75% of terminal surface	SnAg3.0Cu0.5 solder			
	is to be soldered newly	245±5°C, 3±0.3sec.			
	·	(preheating : 80~120°C for 10~30sec.)			
Resistance to	Capacitance change: within ±7.5%	Solder pot : 270±5°C, 10±1sec.			
Soldering Heat	Tan δ, IR : initial spec.				
Vibration Test	Capacitance change : within ± 5% Tan δ, IR : initial spec.	Amplitude: 1.5mm From 10Hz to 55Hz (return: 1min.) 2hours × 3 direction (x, y, z)			
Moisture	Capacitance change: within ±12.5%	With rated voltage			
Resistance	Tan δ : 0.05 max	40±2℃, 90~95%RH, 500+12/-0hrs			
	IR: 500Mohm or 25Mohm × µF				
	Whichever is smaller				
High Temperature	Capacitance change : within ±12.5%	With 200% of the rated voltage			
Resistance	Tan δ : 0.05 max	Max. operating temperature			
	IR: 1,000Mohm or 50Mohm × µF Whichever is smaller	1000+48/-0hrs			
Temperature	Capacitance change: within ±7.5%	1 cycle condition			
Cycling	Tan δ, IR : initial spec.	Min. operating temperature → 25°C			
		→ Max. operating temperature → 25°C			
		5 cycle test			
	•				

X The reliability test condition can be replaced by the corresponding accelerated test condition.

D. Recommended Soldering method:

Reflow (Reflow Peak Temperature : 260+0/-5°C, 10sec. Max)



A Product specifications included in the specifications are effective as of March 1, 2013.

Please be advised that they are standard product specifications for reference only.

We may change, modify or discontinue the product specifications without notice at any time.

So, you need to approve the product specifications before placing an order.

Should you have any question regarding the product specifications,

please contact our sales personnel or application engineers.