

## CF-700 Series

# EcoFoam<sup>™</sup> UL V0 Rated Grey Conductive Foam



### UL VO RATED ECOFOAM™ GREY CONDUCTIVE FOAM

Laird's CF700 Grey offers an innovative approach to traditional shielding and grounding by providing X, Y, and Z-axis conductivity, enhancing the shielding effectiveness required to meet the increasing microprocessor speeds of today's computer, telecommunications, and other electronic equipment. Ecofoam™ can be customized to your application by die-cutting, hole-punching, notching, and so on and is especially useful for odd-shaped applications which are difficult to shield with typical profile gaskets. Ecofoam™ is designed for low-cycling applications such as input/output (I/O) shielding and other non-shear standard connectors.

### **FEATURES**






- · RoHS compliant
- Halogen-free per IEC-61249-2-21 standard
- Excellent z-axis conductivity to provide effective EMI shielding and grounding
- Low compression forces allow for use of lighter materials
- Available with or without conductive PSA
- UL94 V0 Flammability Rating

## **MARKETS**

- Servers
- Cabinet Application
- Network and Telecommunication Equipment
- LCD and Plasma TV
- Medical Equipment
- Desktop Computers
- Printers
- Laptop Computers
- Tablets and Smartphones

### ECOFOAM™ 700-SERIES


THICKNESS	DESIGNATION	
0.5 mm	CF705	
1.0 mm	CF710	
1.5 mm	CF715	
2.0 mm	CF720	



USA: +1.866.928.8181 Europe: +49.0.8031.2460.0 Asia: +86.755.2714.1166

## EcoFoam™ UL VO Rated Grey Conductive Foam

### SHIELDING EFFECTIVENESS



### **PHYSICAL PROPERTIES**


FITTSICAL PROPERTIES			
ITEM	UNIT	VALUE	TEST METHOD
Thickness (Foam w/o CPSA)	mm (±0.2 mm) mm (±0.5 mm)	0.5 1.0, 1.5, 2.0	-
Z-Axis Resistance*	Ω	<0.2	Laird Internal
Shielding Effectiveness (CF720)			MIL-DTL-83528C (modified
300 MHz	dB	89	
3 GHz	dB	109	
30 GHz	dB	106	
Operation Temperature	°C	-40 to 70	-
Hazardous Substance	Compliant with RoHS (Directive 2002/95/EC)		
	Halogen-free per IEC-61249-2-21 Standard		
Shelf Life	12 months at 23°C/ 60% R.H.		

<sup>\*1.0</sup> in<sup>2</sup> sample size, 1000gf loading

Values presented have been determined by standard test methods and are typical values not to be used for specification purposes.

### ORDERING INFORMATION

### PART NUMBER EXAMPLE



### EMI-DS-FOF-ECOFOAM-700-Grey 112415

Any information furnished by Laird and its agents is believed to be accurate and reliable. All specifications are subject to change without notice. Responsibility for the use and application of Laird materials rests with the end user, since Laird and its agents cannot be aware of all potential uses. Laird makes no warranties as to the fitness, merchantability or suitability of any Laird materials or products for any specific or general uses. Laird, Laird Technologies, Inc. or any of its affiliates or agents shall not be liable for incidental or consequential damages of any kind. All Laird products are sold pursuant to the Laird Technologies. Terms and Conditions of sale in effect from time to time, a copy of which will be furnished upon request. © Copyright 2014 Laird Technologies, Inc. and affiliate company thereof. Other product or service names may be the property of third parties. Nothing herein provides a license under any Laird or any third party intellectual property rights.