



# **Specification of Automotive MLCC**

(Reference sheet)

● Supplier : Samsung electro-mechanics

Product : Multi-layer Ceramic Capacitor


● Samsung P/N: CL21C102JBC1PNC

● Description : CAP, 1 nF, 50V, ± 5%, C0G, 0805

● AEC-Q200 Qualified

## A. Dimension

### Dimension



Size	0805 inch
L	2.0±0.1 mm
W	1.25±0.1 mm
Т	0.85±0.1 mm
BW	0.5 +0.2/-0.3 mm

## B. Samsung Part Number

<u>CL</u>	<u>21</u>	<u>C</u>	<u>102</u>	<u>J</u>	<u>B</u>	<u>C</u>	<u>1</u>	<u>P</u>	<u>N</u>	<u>C</u>
1	2	3	4	(5)	6	<b>⑦</b>	8	9	10	11

① Series	Samsung Multi-layer Ceramic C	apacitor	
② Size	0805 (inch code)	L: 2.0±0.1 mm	W: 1.25±0.1 mm
3 Dielectric	COG	8 Inner electrode	Ni
Capacitance	<b>1</b> nF	Termination	Cu
⑤ Capacitance	± 5%	Plating	Sn 100% (Pb Free)
tolerance		Product	Automotive
Rated Voltage	50 V	Special code	Normal
7 Thickness	0.85±0.1 mm	1 Packaging	Cardboard Type, 7" Reel

## C. Reliability Test and Judgement condition

	Performance	Test condition		
High Temperature	Appearance : No abnormal exterior appearance	Unpowered, 1,000hrs @ Max. temperature		
Exposure	Capacitance Change: Within ±2.5% or 0.25pF	Measurement at 24±2hrs after test conclusion		
	whichever is larger			
	Q: 1,000 min.			
	IR : More than 10,000 № or 500 №× μF			
	Whichever is smaller			
Temperature Cycling	Appearance : No abnormal exterior appearance	1,000Cycles		
. , ,	Capacitance Change: Within ±2.5% or 0.25pF	Measurement at 24±2hrs after test conclusion		
	whichever is larger			
	Q: 1,000 min.	1 cycle condition : -55+0/-3 °C (30±3min) → Room Temp. (1min)		
	IR : More than 10,000 № or 500 №×μF	$\rightarrow$ 125+3/-0 °C (30±3min) $\rightarrow$ Room Temp. (1min)		
	Whichever is smaller			
Destructive Physical	No Defects or abnormalities	Per EIA 469		
Analysis				
Humidity Bias	Appearance : No abnormal exterior appearance	1,000hrs 85 ℃/85%RH, Rated Voltage and 1.3~1.5V,		
-	Capacitance Change: Within ±2.5% or 0.25pF	Add 100kohm resistor		
	whichever is larger			
	Q: 200 min.	The charge/discharge current is less than 50mA.		
	IR : More than 500 MΩ or 25 MΩ×μF			
	Whichever is smaller			
High Temperature	Appearance : No abnormal exterior appearance	1,000hrs @ 125 °C, 200% Rated Voltage,		
Operating Life	Capacitance Change: Within ±3% or 0.3pF	Measurement at 24±2hrs after test conclusion		
. •	whichever is larger	The charge/discharge current is less than 50mA.		
	Q: 350 min.			
	IR : More than 1,000 № or 50 №×μF			
	Whichever is smaller			

	Performance	Test condition				
External Visual	No abnormal exterior appearance	Microscope ('10)				
	W/Abin Abo and affind dispersions	Using The polices				
Physical Dimensions	Within the specified dimensions	Using The calipers				
Mechanical Shock	Appearance : No abnormal exterior appearance	Three shocks in each direction should be applied along				
	Capacitance Change: Within ±2.5% or 0.25pF	3 mutually perpendicular axes of the test specimen (18 shocks)				
	whichever is larger	Peak value Duration Wave Velocity				
		1,500G 0.5ms Half sine 4.7m/sec				
	Q, IR: Initial spec.					
Vibration	Appearance : No abnormal exterior appearance	5g's for 20min., 12cycles each of 3 orientations,				
	Capacitance Change: Within ±2.5% or 0.25pF	Use 8"×5" PCB 0.031" Thick 7 secure points on one long side				
	whichever is larger	and 2 secure points at corners of opposite sides. Parts mounted				
		within 2" from any secure point. Test from 10~2,000Hz.				
	Q, IR: Initial spec.					
	Annearance : No observed outsign annearance					
Resistance to	Appearance : No abnormal exterior appearance	preheating: 150°C for 60~120 sec.				
Solder Heat	Capacitance Change: Within ±2.5% or 0.25pF	Solder pot : 260±5 ℃, 10±1sec.				
	whichever is larger Q, IR: Initial spec.					
	Q, IR : Initial spec.  Appearance : No abnormal exterior appearance	A.F.O. 0.000 0.00   I.O.O. IRIO (10.000 F				
ESD	Capacitance Change: Within ±2.5% or 0.25pF	AEC-Q200-002 or ISO/DIS10605				
	whichever is larger					
	Q, IR: Initial spec.					
Solderability	95% of the terminations is to be soldered	a) Preheat at 155°C for 4 hours, Immerse in solder for 5s at 245±5°C				
Solderability	evenly and continuously	b) Steam aging for 8 hours, Immerse in solder for 5s at 245±5 °C				
	and committees,	c) Steam aging for 8 hours, Immerse in solder for 120s at 240±5°C				
		solder: a solution ethanol and rosin				
Electrical	Capacitance : Within specified tolerance	The Capacitance / D.F. should be measured at 25°C,				
Characterization	Q: 1,000 min.	1 kHz ± 10%, 0.5~5 Vrms				
	IR(25°C): More than 100,000 <sup>M</sup> or 1,000 <sup>M</sup> × µF	I.R. should be measured with a DC voltage not exceeding				
	Whichever is smaller	Rated Voltage @25℃, @125℃ for 60~120 sec.				
	IR(125℃): More than 10,000 № or 100 №× <i>µ</i> F					
	Whichever is smaller					
	Dielectric Strength	Dielectric Strength : 300% of the rated voltage for 1~5 seconds				
Board Flex	Appearance : No abnormal exterior appearance	Bending to the limit, 3 mm for 60 seconds				
	Capacitance Change: Within ±5% or 0.5pF					
<b>T</b>	whichever is larger  Appearance : No abnormal exterior appearance	18 N, for 60 sec.				
Terminal	''	10 N, 101 00 500.				
Strength(SMD)	Capacitance Change: Within ±2.5% or 0.25pF whichever is larger					
Beam Load	Destruction value should be exceed 20 N	Beam speed: 0.5±0.05 mm/sec				
Temperature	COG					
Characteristics	From -55 °C to 125 °C, Capacitance change should	be within 0±30ppm/°C				
GIIdidelelistics		50 5250ррпи 0				

## D. Recommended Soldering method :

Reflow ( Reflow Peak Temperature : 260 +0/-5  $^{\circ}$ C, 30sec. ), Meet IPC/JEDEC J-STD-020 D Standard



A Product specifications included in the specifications are effective as of March 1, 2013.

Please be advised that they are standard product specifications for reference only.

We may change, modify or discontinue the product specifications without notice at any time.

So, you need to approve the product specifications before placing an order.

Should you have any question regarding the product specifications, please contact our sales personnel or application engineers.